



TEST REPORT

LAB NO.: (6621)105-0676
FORM NO.: /
DATE IN: Apr 15, 2021
DATE OUT: Apr 21, 2021
NO. OF WORKING DAYS: 5
PAGE 1 OF 3

OVERALL RATING

PASS X
FAIL _____
DATA _____

Vendor:	WUHAN YOUFU INTERNATIONAL TRADE CO.,LTD	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	/
Sample Description:	AAMI SMS ISOLATION GOWN LEVEL 2	Style Description:	/
Color:	Blue	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/
SKU:	/		

Product Category	/
Test Requested	PARTIAL TEST
Previous Report No.	/

Submitted Fiber Content	SMS
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
WATER RESISTANCE: IMPACT PENETRATION TEST	X			
WATER RESISTANCE: HYDROSTATIC PRESSURE TEST	X			

Remark: [BVCPS \(Shanghai\) contact information for this report](#)

Address: [No.168, Guanghua Road, Zhuangqiao Town, Minhang, Shanghai, China.](#)

General Information:

Jojo Li	086-021-24081666*9309, email: jojo-wj.li@cn.bureauveritas.com
Noah Zhang	086-021-24081666*1720, email: Xiaoliang.zhang@cn.bureauveritas.com
Seven Sun	086-021-24081666*9327, email: Seven.sun@cn.bureauveritas.com
Du Shuang	086-021-24081666*1709, email: shuang.du@cn.bureauveritas.com
Challenge Qiao	086-021-24081666*9331, email: challenge.qiao@cn.bureauveritas.com
Lizzy Liao	086-021-24081666*9303, email: lizzy.liao@bureauveritas.com
Sherry Shen	086-021-24081666*9310, email: shirley-ll.shen@cn.bureauveritas.com

Technical Questions:

Pat Liu	086-021-24081745, email: Pat.liu@cn.bureauveritas.com
Rio Zhang	86-21-24081666*9305, email: Rio.Zhang@cn.bureauveritas.com

BUREAU VERITAS
CONSUMER PRODUCTS SERVICES (SHANGHAI)



JULIA YAN
PROGRAM MANAGER

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>				<u>REQUIREMENTS</u>
<u>WATER RESISTANCE: IMPACT PENETRATION TEST</u> (AATCC 42-17)					
	1	2	3	AVERAGE	
FABRIC (GRAM)	0.0	0.0	0.0	0.0	MAX. 1.0 GRAM
SHOULDER (GRAM)		0.1			MAX. 1.0 GRAM
ARM OPENING (GRAM)		0.1			MAX. 1.0 GRAM
SLEEVE (GRAM)		0.2			MAX. 1.0 GRAM
BELT (GRAM)		0.1			MAX. 1.0 GRAM
<u>WATER RESISTANCE: HYDROSTATIC PRESSURE TEST</u> (AATCC 127)					
	1	2	3	AVERAGE	
FABRIC (CMH ₂ O)	57.6	61.6	61.7	60.3	MIN. 20 CMH ₂ O
SHOULDER (CMH ₂ O)		46.7			MIN. 20 CMH ₂ O
ARM OPENING (CMH ₂ O)		57.2			MIN. 20 CMH ₂ O
SLEEVE (CMH ₂ O)		56.0			MIN. 20 CMH ₂ O
BELT (CMH ₂ O)		51.5			MIN. 20 CMH ₂ O



END OF REPORT